

Technical Data Sheet

AGC-SE122



v.240821

Technical Data Sheet	PLA compound for sheet extrusion	AGC-SE122
Description of properties	AGC-SE122 is a thermoplastic compound based on Polylactic Acid (PLA) for sheet extrusion applications. The material is characterised by its flexibility.	

General properties	Method	Unit	Value
Density	ISO 1183	kg/dm ³	1.30
MFI (190 °C; 2.16 kg)	ISO 1133	g/10min	2

Thermal properties	Method	Unit	Value
Melt temperature	Internal	°C	155

Contact
info@agoodchoice.se
Telephone exchange:
+46 31 3000 530

Head Office
Tärnvägen 11
475 40 Hönö Sweden
Post
Box 1006
475 22 Öckerö Sweden

Improve Tec AB
Org.Nr: 559109-2423
VAT.Nr: SE559109-242301

Technical Data Sheet

AGC-SE122



v.240821

Processing recommendations

- Storage and drying conditions are both important for a successful processing of the material.
- Single screw extruders with low compression are recommended. If an irregular melt flow is achieved a melt pump is recommended. Starve-feeding can be necessary to reduce heat of friction in the cylinder.
- Following temperature profile is recommended for the extruder:

Zone	Temperature (°C)
Zone 1	165
Zone 2	170
Zone 3	170
Zone 4	170
Zone 5	175
Zone 6	175
Flange	175
Die	175

Drying of pellets

- It is very important to dry the pellets prior to extrusion. Moisture causes hydrolysis of the polymer during melt processing resulting in deviations in processing performance and reduced mechanical performance of the finished part.
- Drying at 85 °C in a dry-air dryer. Measure the moisture content after drying to verify sufficiently low moisture content.
- The moisture content shall not exceed 0.05% after drying.

Storage of pellets

- Avoid direct contact with air and light.
- It is recommended to keep the packaging sealed until the material is to be used and to reseal the packaging after usage to avoid moisture uptake.

Recommended

- It is recommended to measure the actual melt temperature with a hand-held device before starting production to check if heat of friction occurs.
- Long time stagnation of the material in the cylinder shall be avoided as this can cause degradation. Purging of the cylinder can be made with a low flow PE-HD.

OBS

- The information submitted in this document is based on our current knowledge and experience.

Contact

info@agoodchoice.se
Telephone exchange:
+46 31 3000 530

Head Office

Tärnvägen 11
475 40 Hönö Sweden
Post
Box 1006
475 22 Öckerö Sweden

Improve Tec AB

Org.Nr: 559109-2423
VAT.Nr: SE559109-242301

Technical Data Sheet

AGC-SE122



v.240821

- In view of the many factors that may affect processing and application, these data do not relieve processors of the responsibility of carrying out their own tests and experiments.

Contact

info@agoodchoice.se

Telephone exchange:

+46 31 3000 530

Head Office

Tärnvägen 11
475 40 Hönö Sweden

Post

Box 1006
475 22 Öckerö Sweden

Improve Tec AB

Org.Nr: 559109-2423

VAT.Nr: SE559109-242301